















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	Natural Course Heights 100% Split Face
	PATTERN	2:1 Random Ashlar
	HEIGHTS	Varies from 2"-9" (Full Bed); 2"-6" (Thin Veneer)
	LENGTHS	Random, from 8"-36" (Full Bed); 8"-24" (Thin Veneer)
	DEPTHS	3/4" to 1-1/4" (Thin Veneer)
	COLORS	Beige , Buff , Charcoal , Gray - Grey , Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 sq ft per ton
	WEIGHT	14.9 lbs per square foot (thin veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Formerly known as NSVI's "Luxemburg"; pre-packaged blend of 50% <i>Fond du Lac Country</i> , and 50% <i>Graphite Country</i> .

ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

ASTM C-170

Parallel to Rift, Dry	36000 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101