















SPECIFICATIONS

| | | |
|--|-----------------|---|
|  | GEOLOGY | Limestone |
|  | TYPE | 100% Bedface |
|  | PATTERN | 2:1 Sawn Course Heights Dimensional Ashlar |
|  | HEIGHTS | 2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer |
|  | LENGTHS | Random, from 8"-48" (Full Bed), 8"-24" (Thin Veneer) |
|  | DEPTHS | 3/4" to 1-1/4" (Thin Veneer) |
|  | COLORS | Beige , Buff , Gray - Grey |
|  | COVERAGE | Full Bed Depth Veneer: 35-40 Square Feet Per Ton |
|  | WEIGHT | 13.7 lbs. per square foot. |
|  | FLATS | 10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet |
|  | CORNERS | 10 l/f Box; 100 l/f Crate; 100 l/f pallet, Crated material can exceed 20" |
|  | NOTES | |

ASTM C-97

| | |
|-----------------------|----------|
| Water Absorption % | .31 psi |
| Bulk Specific Gravity | 2.83 psi |

ASTM C-170

| | |
|----------------------------|-----------|
| Parallel to Rift, Dry | 36100 psi |
| Parallel to Rift, Wet | 32000 psi |
| Perpendicular to Rift, Dry | 35800 psi |
| Perpendicular to Rift, Wet | 30000 psi |

ASTM C-99

| | |
|-----------------------|----------|
| Parallel to Rift, Dry | 3770 psi |
| Parallel to Rift, Wet | 3500 psi |

ASTM C-880

| | |
|----------------------------|----------|
| Perpendicular to Rift, Dry | 1780 psi |
| Perpendicular to Rift, Wet | 1730 psi |



GOLD QUARRIER
ANSI/NSC 373-2013
C0290908-101



GOLD FABRICATOR
ANSI/NSC 373-2013
C0289215-101