















**SPECIFICATIONS**

	<b>GEOLOGY</b>	Limestone
	<b>TYPE</b>	70% Splitface (Graphite Country), 30% Bedface (Graphite Manor)
	<b>PATTERN</b>	Natural Course Heights   2:1 Random Ashlar
	<b>HEIGHTS</b>	Varies from 2" - 9" (Full Bed); 2" - 6" (Thin Veneer)
	<b>LENGTHS</b>	Random, 8" - 36" (Full Bed); 8"-24" (Thin Veneer); Crated/palletized material can exceed 20"
	<b>DEPTHS</b>	Thin Veneer: 3/4" to 1-1/4"
	<b>COLORS</b>	Beige, Buff, Charcoal, Gray-Grey, Tan
	<b>COVERAGE</b>	Full Bed Depth Veneer: 35-40 Square Feet Per Ton Also Available in Thin Veneer
	<b>WEIGHT</b>	14.9 lbs. per square foot.
	<b>FLATS</b>	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	<b>CORNERS</b>	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	<b>NOTES</b>	Aka NSVI's "Zurich"; pre-packaged 70% Splitface (Graphite Country), 30% Bedface (Graphite Manor).

**ASTM C-97**

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

**ASTM C-170**

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

**ASTM C-99**

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

**ASTM C-880**

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi

