















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	100% Bedface
	PATTERN	Natural Course Heights 2:1 Random Ashlar
	HEIGHTS	4"-12" random (Full Bed & Thin Veneer)
	LENGTHS	8"-20" (Full Bed); 8"-24" (Thin Veneer); Crated/palletized material can exceed 20"
	DEPTHS	3/4" to 1-1/4" (Thin Veneer)
	COLORS	Beige, Black, Buff, Charcoal, Gray-Grey, Tan
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	14.9 lbs. per square foot.
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	" <i>Graphite Manor</i> " was previously known as the legacy NSVI product, " <i>Stockholm</i> ". Some photos may still show the former product name.

ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi

